



Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

Rec'd EPTO

29 MAR 2003

REC'D 20 OCT 2003

WIPO

PCT

Bescheinigung

Certificate

Attestation


Die angehefteten Unterlagen stimmen mit der ursprünglich eingereichten Fassung der auf dem nächsten Blatt bezeichneten europäischen Patentanmeldung überein.

The attached documents are exact copies of the European patent application described on the following page, as originally filed.

Les documents fixés à cette attestation sont conformes à la version initialement déposée de la demande de brevet européen spécifiée à la page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

02079195.0



BEST AVAILABLE COPY

Der Präsident des Europäischen Patentamts;
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

R C van Dijk



Anmeldung Nr:
Application no.: 02079195.0
Demande no:

Anmeldetag:
Date of filing: 10.10.02
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

Basell Polyolefine GmbH
Brühler Strasse 60
50389 Wesseling
ALLEMAGNE

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.
If no title is shown please refer to the description.
Si aucun titre n'est indiqué se référer à la description.)

Process for the copolymerization of ethylene

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s)
revendiquée(s)
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/
Classification internationale des brevets:

C08F210/00

Am Anmeldetag benannte Vertragstaaten/Contracting states designated at date of
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR IE IT LI LU MC NL PT SE SK TR

FE6056

TITLE:**PROCESS FOR THE COPOLYMERIZATION OF ETHYLENE**

The present invention relates to a process for the copolymerization of ethylene and one or more alpha-olefins of formula $\text{CH}_2=\text{CH}_A$, wherein A is a $\text{C}_2\text{-C}_{20}$ alkyl radical, in the presence of a metallocene catalyst.

It is known that polyethylene can be modified by the addition, during the polymerization reaction, of small quantities of alpha-olefins, generally 1-butene, 1-hexene or 1-octene. This modification gives ethylene copolymers which have short branches along the main chain due to the units derived from the alpha-olefin comonomers. The branches have the effect that the degree of crystallinity and hence the density of the copolymer turn out to be lower than in polyethylene homopolymer. Typically, ethylene copolymers have densities of the order of $0.915\text{-}0.940\text{ g/cm}^3$ associated to advantageous mechanical properties, in particular for the production of films.

The lowering of the degree of crystallinity and of the density of the copolymers depends on the type and quantity of the incorporated alpha-olefin. In general, the greater the quantity of incorporated alpha-olefin, the lower are the resulting degrees of crystallinity and density.

Besides the type and quantity of the incorporated alpha-olefin comonomer, the properties of the copolymer depend on the distribution of the branches along the polymer chain. In particular, a uniform distribution of the branches has relevant effects on the properties of the copolymers. In fact, with the same type and quantity of incorporated alpha-olefin, a higher uniformity of distribution allows lower degrees of crystallinity and density to be obtained.


Metallocene compounds having two bridged cyclopentadienyl groups are known as catalyst components for the homo- and copolymerization reaction of ethylene. A main drawback of the use of metallocene catalysts is that the comonomer incorporation ability is quite low, and therefore it is necessary to use a large excess of comonomer in order to achieve copolymers having the desired comonomer content. Moreover it is often difficult to tune the comonomer content in a copolymer.

Bis indenyl metallocene compounds having the indenyl moieties substituted in 4 position with a substituted phenyl group are known, for example, in WO 98/40331, but they have never been used for obtaining ethylene copolymer.

(FE6056-EP)

Thus it would be desirable to find a metallocene catalyst having an improved balance of properties, i.e. a good comonomer incorporation ability in such a way that it is possible to use a small excess of comonomer in the reactor, maintaining at the same time a good distribution of the comonomer in the molecular chain so to achieve polymer having lower Tg. Moreover, the same time, the metallocene catalyst should produce copolymers having high molecular weight. According to an aspect of the present invention, it is provided a process for producing a copolymer of ethylene containing from 0.1 to 99 % by mol of derived units of one or more alpha-olefins of formula $\text{CH}_2=\text{CHA}$, wherein A is a $\text{C}_2\text{-C}_{20}$ alkyl radical and optionally up to 5% by mol of a polyene, comprising contacting, under polymerization conditions, ethylene, one or more alpha-olefins and optionally said polyene, in the presence of a catalyst system obtainable by contacting:

a) a metallocene compound of formula (I):



(I)

wherein

M is zirconium, titanium or hafnium; preferably M is zirconium or hafnium; more preferably M is zirconium;

X, equal to or different from each other, is a hydrogen atom, a halogen atom, a R, OR, OR'O, OSO_2CF_3 , OCOR , SR, NR_2 or PR_2 group, wherein the R substituents are linear or branched, saturated or unsaturated $\text{C}_1\text{-C}_{20}$ -alkyl, $\text{C}_3\text{-C}_{20}$ -cycloalkyl, $\text{C}_6\text{-C}_{20}$ -aryl, $\text{C}_7\text{-C}_{20}$ -alkylaryl, $\text{C}_7\text{-C}_{20}$ -arylalkyl radicals, optionally containing one or more heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements; and the R'substituent is a $\text{C}_1\text{-C}_{40}$ -alkylidene,

C₆-C₄₀-arylidene, C₇-C₄₀-alkylarylidene or C₇-C₄₀-arylalkylidene; preferably X is a halogen atom, a R, OR'O or OR group; more preferably X is chlorine or methyl;


R¹, equal to or different from each other, is a linear or branched C₁-C₂₀-alkyl radical; preferably R¹ is a linear C₁-C₁₀-alkyl radical more preferably it is methyl or ethyl;

R², equal to or different from each other, is a hydrogen atom or a linear or branched, saturated or unsaturated C₁-C₂₀-alkyl radical;

R³ and R⁴, equal to or different from each other, are hydrogen atoms or linear or branched, saturated or unsaturated C₁-C₂₀-alkyl, C₃-C₂₀-cycloalkyl, C₆-C₂₀-aryl, C₇-C₂₀-alkylaryl or C₇-C₂₀-arylalkyl radicals, optionally containing one or more heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements; or they can form together a condensed saturated or unsaturated 5 or 6 membered ring, optionally containing one or more heteroatoms belonging to groups 13-16 of the Periodic Table of the Elements, said ring optionally bearing one or more substituents; preferably R³ and R⁴ are hydrogen atoms, methyl groups or they form a condensed saturated or unsaturated 5 or 6 membered ring;

R⁵ and R⁶, equal to or different from each other, are hydrogen atoms or linear or branched, saturated or unsaturated C₁-C₂₀-alkyl, C₃-C₂₀-cycloalkyl, C₆-C₂₀-aryl, C₇-C₂₀-alkylaryl, or C₇-C₂₀-arylalkyl radicals, optionally containing one or more heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements; or they can form together a condensed saturated or unsaturated 5 or 6 membered ring, optionally containing one or more heteroatoms belonging to groups 13-16 of the Periodic Table of the Elements, said ring optionally bearing one or more substituents; preferably R⁵ and R⁶ are C₁-C₂₀-alkyl or C₆-C₂₀-aryl radicals; more preferably they are methyl or phenyl;

Q is a radical of formula (II), which is bonded to the indenyl at the position marked by the symbol *;



wherein
(FE6056-EP)

T^1, T^2, T^3, T^4 and T^5 , equal to or different from each other, are carbon atoms (C) or nitrogen atoms (N);

m^1, m^2, m^3, m^4 and m^5 are 0 or 1; more precisely each of m^1, m^2, m^3, m^4 and m^5 is 0 when the correspondent T^1, T^2, T^3, T^4 and T^5 is a nitrogen atom and it is 1 when the correspondent T^1, T^2, T^3, T^4 and T^5 is a carbon atom;


R^7, R^8, R^9, R^{10} and R^{11} , equal to or different from each other, are hydrogen atoms or linear or branched, saturated or unsaturated C_1 - C_{20} -alkyl, C_3 - C_{20} -cycloalkyl, C_6 - C_{20} -aryl, C_7 - C_{20} -alkylaryl, C_7 - C_{20} -arylalkyl radicals, optionally containing one or more heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements; or they can form together a condensed saturated or unsaturated 5 or 6 membered ring, optionally containing one or more heteroatoms belonging to groups 13-16 of the Periodic Table of the Elements; said rings can bear one or more substituents; with the provisos that at least one of R^7, R^8, R^9, R^{10} and R^{11} is different from hydrogen atom, and that no more than two of T^1, T^2, T^3, T^4 and T^5 are nitrogen atoms;

- b) an alumoxane or a compound capable of forming an alkyl metallocene cation; and optionally
- c) an organo aluminum compound.

In a preferred embodiment, R^9 is a linear or branched, saturated or unsaturated C_1 - C_{20} -alkyl, C_3 - C_{20} -cycloalkyl, C_6 - C_{20} -aryl, C_7 - C_{20} -alkylaryl or C_7 - C_{20} -arylalkyl radical; and R^7, R^8, R^{10} and R^{11} are hydrogen atoms.

In another preferred embodiment R^8 and R^{10} are a linear or branched, saturated or unsaturated C_1 - C_{20} -alkyl, C_3 - C_{20} -cycloalkyl, C_6 - C_{20} -aryl, C_7 - C_{20} -alkylaryl, C_7 - C_{20} -arylalkyl radicals; and R^7, R^9 and R^{11} are hydrogen atoms;

A preferred radical belonging to formula (II) has formula (IIa) being bonded to the indenyl at the position indicated by the symbol *:




(IIa)

wherein

R^9 is a branched, saturated or unsaturated C_1 - C_{20} -alkyl or C_6 - C_{20} -aryl radical; more preferably R^9 is a phenyl group, optionally substituted with one or more C_1 - C_{10} alkyl groups, or a group of formula $C(R^{12})_3$ wherein R^{12} , same or different, is a linear or branched, saturated or unsaturated C_1 - C_6 -alkyl radical; preferably R^{12} is methyl.

A further preferred radical belonging to formula (II) has formula (IIb) being bonded to the indenyl at the position indicated by the symbol *:




(IIb)

wherein

R^8 and R^{10} are a branched, saturated or unsaturated C_1 - C_{20} -alkyl or a CF_3 radical; more preferably they are a group of formula $C(R^{12})_3$ wherein R^{12} has been described above;

R^9 is a hydrogen atom or a linear or branched, saturated or unsaturated C_1 - C_{20} -alkyl or C_6 - C_{20} -aryl radical optionally containing one or more heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements; preferably R^9 is a hydrogen atom.

A further preferred radical belonging to formula (II) has formula (IIc) being bonded to the indenyl at the position indicated by the symbol *:




(IIc)

wherein

at least one among R^8 , R^9 , R^{10} and R^{11} is different from a hydrogen atom; preferably R^{10} and R^{11} are hydrogen atoms; preferably R^8 and R^9 are a linear or branched, saturated or unsaturated C_1 - C_{20} -alkyl radical, or they form a saturated or unsaturated condensed 5 or 6 membered ring optionally containing one or more heteroatoms belonging to groups 13-16 of the

Periodic Table of the Elements, said ring optionally bearing one or more substituents; more preferably R^8 and R^9 form a saturated or unsaturated condensed 5 or 6 membered ring optionally containing one or more heteroatoms belonging to groups 15-16 of the Periodic table;

A further preferred radical belonging to formula (II) has formula (II_d), being bonded to the indenyl at the position indicated by the symbol *:




(II_d)

wherein:

R^{10} and R^{11} are a linear or branched, saturated or unsaturated C_1 - C_{20} -alkyl radical, or they form a saturated or unsaturated condensed 5 or 6 membered ring optionally containing one or more heteroatoms belonging to groups 13-16 of the Periodic Table of the Elements, said ring optionally bearing one or more substituents; more preferably R^{10} and R^{11} form a saturated or unsaturated condensed 5 or 6 membered ring optionally containing one or more heteroatoms belonging to groups 15-16 of the Periodic table; such as phenyl ring, pyrrole ring, pyridine ring; said catalyst system further comprising:

Preferably the metallocene compound of formula (I) is in the racemic form.

Non limitative examples of compound of formula (I) are:



Wherein W and W' are methyl or ethyl.


(FE6056-EP)

Compounds of formula (1) are well known in the art. They can be prepared, for example, as described in to WO 98/40331.

Alumoxanes used as component b) can be obtained by reacting water with an organo-aluminium compound of formula H_jAlU_{3-j} or $H_jAl_2U_{6-j}$, where the U substituents, same or different, are hydrogen atoms, halogen atoms, C_1 - C_{20} -alkyl, C_3 - C_{20} -cyclalkyl, C_6 - C_{20} -aryl, C_7 - C_{20} -alkylaryl or C_7 - C_{20} -arylalkyl radical, optionally containing silicon or germanium atoms, with the proviso that at least one U is different from halogen, and j ranges from 0 to 1, being also a non-integer number. In this reaction the molar ratio of Al/water is preferably comprised between 1:1 and 100:1.


The molar ratio between aluminium and the metal of the metallocene generally is comprised between about 10:1 and about 30000:1, preferably between about 100:1 and about 5000:1.

The alumoxanes used in the catalyst according to the invention are considered to be linear, branched or cyclic compounds containing at least one group of the type:




wherein the substituents U, same or different, are described above.

In particular, alumoxanes of the formula:



can be used in the case of linear compounds, wherein n^1 is 0 or an integer of from 1 to 40 and the substituents U are defined as above, or alumoxanes of the formula:



can be used in the case of cyclic compounds, wherein n^2 is an integer from 2 to 40 and the U substituents are defined as above.

Examples of alumoxanes suitable for use according to the present invention are methylalumoxane (MAO), tetra-(isobutyl)alumoxane (TIBAO), tetra-(2,4,4-trimethyl-pentyl)alumoxane (TIOAO), tetra-(2,3-dimethylbutyl)alumoxane (TDMBAO) and tetra-(2,3,3-trimethylbutyl)alumoxane (TTMBAO).

Particularly interesting alumoxanes are those described in WO 99/21899 and in WO01/21674 in (FE6056-EP)

which the alkyl and aryl groups have specific branched patterns.

Non-limiting examples of aluminium compounds according to WO 99/21899 and WO01/21674 are: tris(2,3,3-trimethyl-butyl)aluminium, tris(2,3-dimethyl-hexyl)aluminium, tris(2,3-dimethyl-butyl)aluminium, tris(2,3-dimethyl-pentyl)aluminium, tris(2,3-dimethyl-heptyl)aluminium, tris(2-methyl-3-ethyl-pentyl)aluminium, tris(2-methyl-3-ethyl-hexyl)aluminium, tris(2-methyl-3-ethyl-heptyl)aluminium, tris(2-methyl-3-propyl-hexyl)aluminium, tris(2-ethyl-3-methyl-butyl)aluminium, tris(2-ethyl-3-methyl-pentyl)aluminium, tris(2,3-diethyl-pentyl)aluminium, tris(2-propyl-3-methyl-butyl)aluminium, tris(2-isopropyl-3-methyl-butyl)aluminium, tris(2-isobutyl-3-methyl-pentyl)aluminium, tris(2,3,3-trimethyl-pentyl)aluminium, tris(2,3,3-trimethyl-hexyl)aluminium, tris(2-ethyl-3,3-dimethyl-butyl)aluminium, tris(2-ethyl-3,3-dimethyl-pentyl)aluminium, tris(2-isopropyl-3,3-dimethyl-butyl)aluminium, tris(2-trimethylsilyl-propyl)aluminium, tris(2-methyl-3-phenyl-butyl)aluminium, tris(2-ethyl-3-phenyl-butyl)aluminium, tris(2,3-dimethyl-3-phenyl-butyl)aluminium, tris(2-phenyl-propyl)aluminium, tris[2-(4-fluorophenyl)-propyl]aluminium, tris[2-(4-chloro-phenyl)-propyl]aluminium, tris[2-(3-isopropyl-phenyl)-propyl]aluminium, tris(2-phenyl-butyl)aluminium, tris(3-methyl-2-phenyl-butyl)aluminium, tris(2-phenyl-pentyl)aluminium, tris[2-(pentafluorophenyl)-propyl]aluminium, tris[2,2-diphenyl-ethyl]aluminium and tris[2-phenyl-2-methyl-propyl]aluminium, as well as the corresponding compounds wherein one of the hydrocarbyl groups is replaced with a hydrogen atom, and those wherein one or two of the hydrocarbyl groups are replaced with an isobutyl group.

Amongst the above aluminium compounds, trimethylaluminium (TMA), triisobutylaluminium (TIBAL), tris(2,4,4-trimethyl-pentyl)aluminium (TIOA), tris(2,3-dimethylbutyl)aluminium (TDMBA) and tris(2,3,3-trimethylbutyl)aluminium (TTMBA) are preferred.

Non-limiting examples of compounds able to form an alkylmetallocene cation are compounds of formula D^+E^- , wherein D^+ is a Brønsted acid, able to donate a proton and to react irreversibly with a substituent X of the metallocene of formula (I) and E^- is a compatible anion, which is able to stabilize the active catalytic species originating from the reaction of the two compounds, and which is sufficiently labile to be able to be removed by an olefinic monomer. Preferably, the anion E^- comprises of one or more boron atoms. More preferably, the anion E^- is an anion of the formula $BAr_4^{(-)}$, wherein the substituents Ar which can be identical or different are aryl radicals such as phenyl, pentafluorophenyl or bis(trifluoromethyl)phenyl. Tetrakis-pentafluorophenyl borate is particularly preferred examples of these compounds are described in WO 91/02012. Moreover,

(FE6056-EP)

compounds of the formula BAr_3 can conveniently be used. Compounds of this type are described, for example, in the published International patent application WO 92/00333. Other examples of compounds able to form an alkylmetallocene cation are compounds of formula BAr_3P wherein P is a substituted or unsubstituted pyrrol radicals. These compounds are described in WO01/62764. Other examples of cocatalyst can be found in EP 775707 and DE 19917985. Compounds containing boron atoms can be conveniently supported according to the description of WO 01/47635 and WO 01/48035. All these compounds containing boron atoms can be used in a molar ratio between boron and the metal of the metallocene comprised between about 1:1 and about 10:1; preferably 1:1 and 2:1; more preferably about 1:1.

Non limiting examples of compounds of formula D^+E^- are:

Triethylammoniumtetra(phenyl)borate,
Tributylammoniumtetra(phenyl)borate,
Trimethylammoniumtetra(tolyl)borate,
Tributylammoniumtetra(tolyl)borate,
Tributylammoniumtetra(pentafluorophenyl)borate,
Tributylammoniumtetra(pentafluorophenyl)aluminate,
Tripropylammoniumtetra(dimethylphenyl)borate,
Tributylammoniumtetra(trifluoromethylphenyl)borate,
Tributylammoniumtetra(4-fluorophenyl)borate,
N,N-Dimethylbenzylammonium-tetrakis(pentafluorophenyl)borate,
N,N-Dimethylhexylammonium-tetrakis(pentafluorophenyl)borate,
N,N-Dimethylaniliniumtetra(phenyl)borate,
N,N-Diethylaniliniumtetra(phenyl)borate,
N,N-Dimethylaniliniumtetrakis(pentafluorophenyl)borate,
N,N-Dimethylaniliniumtetrakis(pentafluorophenyl)aluminate,
N,N-Dimethylbenzylammonium-tetrakis(pentafluorophenyl)borate,
N,N-Dimethylhexylammonium-tetrakis(pentafluorophenyl)borate,
Di(propyl)ammoniumtetrakis(pentafluorophenyl)borate,
Di(cyclohexyl)ammoniumtetrakis(pentafluorophenyl)borate,
Triphenylphosphoniumtetrakis(phenyl)borate,
Triethylphosphoniumtetrakis(phenyl)borate,

(FE6056-EP)

Diphenylphosphoniumtetrakis(phenyl)borate,
 Tri(methylphenyl)phosphoniumtetrakis(phenyl)borate,
 Tri(dimethylphenyl)phosphoniumtetrakis(phenyl)borate,
 Triphenylcarbeniumtetrakis(pentafluorophenyl)borate,
 Triphenylcarbeniumtetrakis(pentafluorophenyl)aluminate,
 Triphenylcarbeniumtetrakis(phenyl)aluminate,
 Ferroceniumtetrakis(pentafluorophenyl)borate,
 Ferroceniumtetrakis(pentafluorophenyl)aluminate.
 Triphenylcarbeniumtetrakis(pentafluorophenyl)borate, and
 N,N-Dimethylaniliniumtetrakis(pentafluorophenyl)borate.

Organic aluminum compounds used as compound c) are those of formula H_3AlU_{3-j} or $H_3Al_2U_{6-j}$ described above.

The catalysts system used in the process of the present invention can also be supported on an inert carrier. This is achieved by depositing the metallocene compound a) or the product of the reaction thereof with the component b), or the component b) and then the metallocene compound a) on an inert support such as, for example, silica, alumina, Al-Si, Al-Mg mixed oxides, magnesium halides, styrene/divinylbenzene copolymers, polyethylene or polypropylene. The supportation process is carried out in an inert solvent such as an hydrocarbon (for example toluene, hexane, pentane or propane) at a temperature ranging from 0°C to 100°C and preferably at a temperature ranging from 25°C to 90°C.

A suitable class of inert supports is constituted by porous organic supports functionalized with groups having active hydrogen atoms. Particularly suitable are those in which the organic support is a partially crosslinked styrene polymer. Supports of this type are described in European application EP-633 272.

Another class of inert supports particularly suitable for use according to the invention is that of polyolefin porous prepolymers, particularly polyethylene.

A further suitable class of inert supports for use according to the invention is that of porous magnesium halides, such as those described in International application WO 95/32995.

The solid compound thus obtained, optionally in combination with alkylaluminium compound, either as such or prereacted with water, can be usefully employed in gas-phase polymerization.

The process for the polymerization of olefins according to the invention can be carried out in the

(FE6056-EP)

liquid phase, in the presence or absence of an inert hydrocarbon solvent, or in the gas phase. The hydrocarbon solvent can either be aromatic such as toluene, or aliphatic such as propane, hexane, heptane, isobutane or cyclohexane.

The polymerization temperature is generally comprised between -100°C and $+100^{\circ}\text{C}$ and, particularly between 10°C and $+90^{\circ}\text{C}$. The polymerization pressure is generally comprised between 0,5 and 100 bar.

The lower the polymerization temperature, the higher are the resulting molecular weights of the polymers obtained.

The polymerization yields depend on the purity of the metallocene compound of the catalyst system. The metallocene compounds obtained by the process of the invention can therefore be used as such or can be subjected to purification treatments.

The components of the catalyst system can be brought into contact with each other before the polymerization. The pre-contact concentrations are generally between 0.1 and 10^{-8} mol/l for the metallocene component a), while they are generally between 2 and 10^{-8} mol/l for the component b). The pre-contact is generally effected in the presence of a hydrocarbon solvent and, if appropriate, of small quantities of monomer. In the pre-contact it is also possible to use a non-polymerizable olefin, such as isobutene, 2-butene and the like.

The molecular weight distribution can be varied by using mixtures of different metallocene compounds or by carrying out the polymerization in several stages which differ as to the polymerization temperature and/or the concentrations of the molecular weight regulators and/or the monomers concentration. Moreover, by carrying out the polymerization process by using a combination of two different metallocene compounds of formula (I), a polymer endowed with a broad molecular weight distribution is produced.

In the copolymers obtainable by the process of the invention, the content of ethylene derived units is between 99.9% by mol and 1% by mol; preferably it is between 99 % by mol and 70% by mol; and more preferably it is between 95% by mol and 60% by mol.

The content of alpha-olefins derived units is between 0.1% by mol and 99% by mol; preferably it is between 1 % by mol and 30% by mol; and more preferably it is between 5% by mol and 40% by mol.

Non-limiting examples of alpha-olefins of formula $\text{CH}_2=\text{CH}_A$ which can be used as alpha-olefins in the process of the invention are 1-butene, 1-pentene, 4-methyl-1-pentene, 1-hexene, 1-octene, (FE6056-BP)

4,6-dimethyl-1-heptene, 1-decene, 1-dodecene, 1-tetradecene, 1-hexadecene, 1-octadecene and 1-eicosene. Preferred comonomers are 1-pentene, 1-hexene and 1-octene.

The content of polyene derived units is preferably comprised between 0% and 5% by mol and, more preferably between 0 and 3 by mol%.

The polyenes that can be used as comonomers in the copolymers according to the present invention are included in the following classes:

- non-conjugated diolefins able to cyclopolymerize such as, for example, 1,5-hexadiene, 1,6-heptadiene, 2-methyl-1,5-hexadiene;
- dienes capable of giving unsaturated monomeric units, in particular conjugated dienes such as, for example, butadiene and isoprene, and linear non-conjugated dienes, such as, for example, trans 1,4-hexadiene, cis 1,4-hexadiene, 6-methyl-1,5-heptadiene, 3,7-dimethyl-1,6-octadiene, 11-methyl-1,10-dodecadiene, and cyclic non-conjugated dienes such as 5-ethylidene-2-norbornene.

With a process of the present invention it is possible to achieve a good balance of different properties. In fact, with the process of the present invention the incorporation of the comonomer is high and this allows the use of a smaller excess of comonomer in the reactor and to achieve a better tunable process. At the same time the comonomer is well distributed, as shown by the r_1 and r_2 values and by the glass transition temperature. Moreover the copolymers obtained with the process of the present invention have a high molecular weight (I.V.) that makes the process object of the present invention suitable for an industrial use.

The intrinsic viscosity values are generally higher than 0.5 dL/g, preferably they are between 1.5 to 10 dL/g; and more preferably between 2 and 4 dL/g.

The following examples are given for illustrative purposes and do not intend to limit the invention.

EXAMPLES

General procedures

All operations were performed under nitrogen by using conventional Schlenk-line techniques. Heptane and toluene were purified by degassing with N_2 and passing over activated (8 hours, N_2 purge, 300 °C) Al_2O_3 , and stored under nitrogen. 1-hexene (Aldrich) was dried over alumina and distilled over $LiAlH_4$. Polymerization grade ethylene was obtained from the Basell Ferrara plant. MAO (methylalumoxane, Witco) was purchased as a 10 wt.-% solution in toluene, dried under (FE6056-EP)

vacuum to remove most of the free trimethylaluminum and used as 1 M toluene solution. TIBA ($\text{Al}(i\text{-Bu})_3$, Witco) was used as 1 M toluene solution.

^1H NMR spectra of copolymers were recorded at 120 °C on a Bruker DPX-400 spectrometer operating at 100.61 MHz, in the Fourier transform mode. The samples were prepared by dissolving 10 mg of copolymer in 0.5 mL of 1,1,2,2-tetrachloroethane- d_2 at 120 °C. The peak of C_2HDCl_2 (5.95 ppm) was used as internal standard. Each spectrum was acquired with a 45° pulse and 20 seconds of delay between pulses. About 16 transients were stored in 32K data points using a spectral window of 16 ppm.

The 1-hexene content in the copolymers was calculated from the methylene and methyne peak integral (I_A) and the methyl peak integral (I_B), by applying the following relationships:

$$[C_6] = I_B/3$$

$$[C_2] = (I_A - 3I_B)/4$$

$$\Sigma = [C_6] + [C_2] = (I_B/3) + (I_A - 3I_B)/4$$

$$C_{6\text{ copol}} (\% \text{ mol}) = 100 \times [C_6] / \Sigma = 100 \times I_B / 3\Sigma$$

The molecular weight distribution was determined on a WATERS 150 C using the following chromatographic conditions:

Columns: 3x SODEX AT 806 MS; 1x SODEX UT 807; 1x SODEX AT-G;
 Solvent: 1,2,4 trichlorobenzene (+0.025% 2,6-di-*tert*-butyl-4-methyl-phenol)
 Flow rate: 0.6-1 mL/min
 Temperature: 135°C
 Detector: Infrared at $\lambda \cong 3.5 \mu\text{m}$
 Calibration: Universal Calibration with PS-Standard

The intrinsic viscosity (I.V.) was measured in decaline (DHN) at 135°C.

The melting points (T_m) and glass transition temperatures (T_g) were determined on a DSC30 Mettler instrument equipped with a cooling device, by heating the sample from 25 °C to 200 °C at 20 °C/min, holding for 10 min at 200 °C, cooling from 200 °C to -140 °C, holding for 2 min at -140 °C, heating from -140 °C to 200 °C at 20 °C/min. The reported values are those determined from the second heating scan.

In cases in which crystallization phenomena overlap with the glass transition, for a better determination of the T_g value, the samples were heated to 200°C at 20°C/minute, quickly cooled to a temperature lower than the T_m (usually 20, 0 or -20°C) at 200°C/minute, and kept at this (FE6056-EP)


temperature for 720 minutes. The samples were then further quickly cooled to $-140\text{ }^{\circ}\text{C}$ at $200^{\circ}\text{C}/\text{minute}$ and finally re-heated to 200°C at $20^{\circ}\text{C}/\text{minute}$. The whole process was carried out under nitrogen flow of $20\text{ mL}/\text{minute}$.

Determination of liquid phase composition

The liquid phase composition was calculated from the Redlich-Kwong-Soave equations. This set of thermodynamic equations was selected among those available in Aspen PlusTM (commercialized by Aspen Technology Inc., Release 9) on the basis of a comparison with the experimental results. The concentrations of the comonomers were hence calculated.


METALLOCENE COMPOUNDS

Dimethylsilylbis(2-methyl-4-phenyl-1-indenyl)zirconium dichloride [C1]



was prepared according to USP 5,786,432.

dimethylsilylbis(2-methyl-4(4-tertbutyl-phenyl)-1-indenyl)zirconium dichloride [A1]



was prepared according to WO 98/40331

Polymerization Examples 1-6

General procedure

Ethylene/1-hexene copolymerizations were carried out in a 260-mL Büchi glass autoclave equipped with magnetic stirrer, thermocouple and feeding line for the monomer, purified with (TE6056-EP)




Table 1

Ex	metall amount	1-hexene liquid phase	Time	Yield	Activity	1-hex copol (^1H NMR)	$r_1 r_2$	I.V.	Mw/Mn	T_g	T_m
	μmol	(g)	(%mol)	(%wt)	(g)	$\text{Kg}_{\text{pol}}/(\text{mmol}_{\text{Zr}}\cdot\text{h})$	(%mol)	(dL/g)		$^{\circ}\text{C}$	$^{\circ}\text{C}$
1*	C1 0.2	1.32	22.8	46.9	5	30.6	10.3	2.96	2.48	-44.3	82.5
2*	C1 0.3	3.29	42.4	68.8	5	51.2	21.5	2.17	2.39	-51.3	n.d.
3*	C1 0.3	6.59	59.3	81.4	7	30.3	32.6	1.72	2.51	-56.0	n.d.
4	Al 0.3	1.32	22.8	46.9	3	66.0	15.8	2.8	2.59	-51.6	56.6
5	Al 0.3	3.29	42.4	68.8	5	43.6	26.5	2.27	2.49	-57.1	n.d.
6	Al 0.3	6.59	59.3	81.4	5	31.2	32.3	1.92	2.46	-58.2	n.d.

* comparison examples.
n.d. = not determinable;

Claims

1. A process for producing a polymer of ethylene containing from 0.1 to 99 % by mol of derived units of one or more of alpha-olefins of formula $\text{CH}_2=\text{CHA}$, wherein A is a $\text{C}_2\text{-C}_{20}$ alkyl radical and optionally up to 5% by mol polyene, comprising contacting, under polymerization conditions, ethylene, one or more alpha-olefins and optionally said polyene, in the presence of a catalyst system obtainable by contacting:
 - a) a metallocene compound of formula (I):



wherein

M is zirconium, titanium or hafnium;

X, equal to or different from each other, is a hydrogen atom, a halogen atom, a R, OR, OR'O, OSO_2CF_3 , OCOR , SR, NR_2 or PR_2 group, wherein the R substituents are linear or branched, saturated or unsaturated $\text{C}_1\text{-C}_{20}$ -alkyl, $\text{C}_3\text{-C}_{20}$ -cycloalkyl, $\text{C}_6\text{-C}_{20}$ -aryl, $\text{C}_7\text{-C}_{20}$ -alkylaryl or $\text{C}_7\text{-C}_{20}$ -arylalkyl radicals, optionally containing one or more heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements; and the R'substituent is a $\text{C}_1\text{-C}_{40}$ -alkylidene, $\text{C}_6\text{-C}_{40}$ -arylidene, $\text{C}_7\text{-C}_{40}$ -alkylarylidene or $\text{C}_7\text{-C}_{40}$ -arylalkylidene;


R^1 , equal to or different from each other, are a linear or branched $\text{C}_1\text{-C}_{20}$ -alkyl radical;

R^2 , equal to or different from each other, is a hydrogen atom or a linear or branched, saturated or unsaturated $\text{C}_1\text{-C}_{20}$ -alkyl radical;

R^3 and R^4 , equal to or different from each other, are hydrogen atoms or linear or branched, saturated or unsaturated C_1 - C_{20} -alkyl, C_3 - C_{20} -cycloalkyl, C_6 - C_{20} -aryl, C_7 - C_{20} -alkylaryl or C_7 - C_{20} -arylalkyl radicals, optionally containing one or more heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements; or they can form together a condensed saturated or unsaturated 5 or 6 membered ring, optionally containing one or more heteroatoms belonging to groups 13-16 of the Periodic Table of the Elements, said ring optionally bearing one or more substituents;

R^5 and R^6 , equal to or different from each other, are hydrogen atoms or linear or branched, saturated or unsaturated C_1 - C_{20} -alkyl, C_3 - C_{20} -cycloalkyl, C_6 - C_{20} -aryl, C_7 - C_{20} -alkylaryl or C_7 - C_{20} -arylalkyl radicals, optionally containing one or more heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements; or they can form together a condensed saturated or unsaturated 5 or 6 membered ring, optionally containing one or more heteroatoms belonging to groups 13-16 of the Periodic Table of the Elements, said ring optionally bearing one or more substituents;

Q is a radical of formula (II) which is bonded to the indenyl at the position marked by the symbol *;



(II)


wherein

T^1 , T^2 , T^3 , T^4 and T^5 , same or different, are carbon atoms (C) or nitrogen atoms (N);

m^1 , m^2 , m^3 , m^4 and m^5 are 0 or 1; m^1 , m^2 , m^3 , m^4 and m^5 being 0 when the correspondent T^1 , T^2 , T^3 , T^4 and T^5 is a nitrogen atom, and being 1 when the correspondent T^1 , T^2 , T^3 , T^4 and T^5 is a carbon atom;

R^7, R^8, R^9, R^{10} and R^{11} , equal to or different from each other, are hydrogen atoms or linear or branched, saturated or unsaturated C_1 - C_{20} -alkyl, C_3 - C_{20} -cycloalkyl, C_6 - C_{20} -aryl, C_7 - C_{20} -alkylaryl or C_7 - C_{20} -arylalkyl radicals, optionally containing one or more heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements; or they can form together a condensed saturated or unsaturated 5 or 6 membered ring, optionally containing one or more heteroatoms belonging to groups 13-16 of the Periodic Table of the Elements; said rings can bear one or more substituents; with the provisos that at least one of R^7, R^8, R^9, R^{10} and R^{11} is different from hydrogen atom, and that no more than two of T^1, T^2, T^3, T^4 and T^5 are nitrogen atoms; and

- b) an alumoxane or a compound capable of forming an alkyl metallocene cation.
2. The process according to claim 1 wherein the catalyst system further comprises an organo aluminum compound.
 3. The process according to claims 1 or 2 wherein in the compound of formula (I), X is a halogen atom, a R, OR' O or OR group; R^3 and R^4 are hydrogen atoms, methyl or they form a condensed saturated or unsaturated 5 or 6 membered ring; R^5 and R^6 are C_1 - C_{20} -alkyl or C_6 - C_{20} -aryl radicals.
 4. The process according to anyone of claims 1-3 wherein in the radical of formula (II) R^9 is a linear or branched, saturated or unsaturated C_1 - C_{20} -alkyl, C_3 - C_{20} -cycloalkyl, C_6 - C_{20} -aryl, C_7 - C_{20} -alkylaryl or C_7 - C_{20} -arylalkyl radicals; and R^7, R^8, R^{10} and R^{11} are hydrogen atoms.
 5. The process according to anyone of claims 1-3 wherein in the radical of formula (II) R^8 and R^{10} are a linear or branched, saturated or unsaturated C_1 - C_{20} -alkyl, C_3 - C_{20} -cycloalkyl, C_6 - C_{20} -aryl, C_7 - C_{20} -alkylaryl, C_7 - C_{20} -arylalkyl radicals; and R^7, R^9 and R^{11} are hydrogen atoms.
 6. The process according to claim 4 wherein the radical belonging to formula (II) has formula (IIa), being bonded to the indenyl at the position indicated by the symbol *:




(IIa)

wherein:

R^9 is a branched, saturated or unsaturated C_1 - C_{20} -alkyl or C_6 - C_{20} -aryl radical;

7. The process according to claim 6 wherein R^9 is a phenyl group, optionally substituted with one or more C_1 - C_{10} alkyl groups, or a group of formula $C(R^{12})_3$ wherein R^{12} , same or different, is a linear or branched, saturated or unsaturated C_1 - C_6 -alkyl radical.
8. The process according to claim 1 wherein the radical belonging to formula (II) has formula (IIb) being bonded to the indenyl at the position indicated by the symbol *




(IIb)

wherein

R^8 and R^{10} , are a branched, saturated or unsaturated C_1 - C_{20} -alkyl or a CF_3 radical; R^9 is a hydrogen atom or a linear or branched, saturated or unsaturated C_1 - C_{20} -alkyl or C_6 - C_{20} -aryl radical, optionally containing one or more heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements.


9. The process according to claim 8 wherein R^8 and R^{10} are a group of formula $C(R^{12})_3$ wherein R^{12} , same or different, is a linear or branched, saturated or unsaturated C_1 - C_6 -alkyl radical and R^9 is a hydrogen atom.
10. The process according to anyone of claims 1-3 wherein the radical belonging to formula (II) has formula (IIc), being bonded to the indenyl at the position indicated by the symbol *:



(IIc)

wherein R^8 , R^9 , R^{10} and R^{11} have the meaning reported in claim 1 and at least one among R^8 , R^9 , R^{10} and R^{11} is different from a hydrogen atom.

11. The process according to claim 10 wherein R^{10} and R^{11} are hydrogen atoms; R^8 and R^9 are a linear or branched, saturated or unsaturated C_1 - C_{20} -alkyl radical, or they form a saturated or unsaturated condensed 5 or 6 membered ring optionally containing one or more heteroatoms belonging to groups 13-16 of the Periodic Table of the Elements, said ring optionally bearing one or more substituents.
12. The process according to anyone of claims 1-3 wherein the radical belonging to formula (II) has formula (II_d) being bonded to the indenyl at the position indicated by the symbol *:



(II_d)

wherein:


R^{10} and R^{11} are a linear or branched, saturated or unsaturated C_1 - C_{20} -alkyl radical, or they form a saturated or unsaturated condensed 5 or 6 membered ring optionally containing one or more heteroatoms belonging to groups 13-16 of the Periodic Table of the Elements, said ring optionally bearing one or more substituents.

13. The process according to anyone of claims 1-12 wherein the alpha-olefin is 1-butene, 1-pentene, 4-methyl-1-pentene, 1-hexene, 1-octene, 4,6-dimethyl-1-heptene, 1-decene, 1-dodecene, 1-tetradecene, 1-hexadecene, 1-octadecene or 1-eicosene.
14. The process according to claims 13 wherein the alpha-olefin is 1-pentene, 1-hexene or 1-octene.

Abstract

A process for producing a copolymer of ethylene containing from 0.1 to 99 % by mol of one or more derived units of alpha-olefins of formula $\text{CH}_2=\text{CHA}$, wherein A is a $\text{C}_2\text{-C}_{20}$ alkyl radical, comprising contacting, under polymerization conditions, ethylene and one or more alpha-olefins in the presence of a catalyst system obtainable by contacting:


a) a metallocene compound of formula (I):



wherein

M is zirconium, titanium or hafnium; X, same or different, is a hydrogen atom, a halogen atom, or an hydrocarbon group; R^1 , is a hydrocarbon group; R^2 , R^3 , R^4 , R^5 and R^6 , are hydrogen atoms or hydrocarbon groups;

Q is a radical of formula (II), being bonded to the indenyl at the position marked by the symbol *;



wherein: T^1 , T^2 , T^3 , T^4 and T^5 , are carbon atoms (C) or nitrogen atoms (N); m^1 , m^2 , m^3 , m^4 and m^5 are 0 or 1; R^7 , R^8 , R^9 , R^{10} and R^{11} are hydrogen atoms or hydrocarbon groups; and b) an alumoxane or a compound capable of forming an alkyl metallocene cation.

PCT Application
EP0310107



**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☒ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.